



# Oxidation-Reduction Resistance of Advanced Copper Alloys

L. Thomas-Ogbuji and D.L. Humphrey  
QSS Group, Inc., Cleveland, Ohio

J.A. Setlock  
Case Western Reserve University, Cleveland, Ohio

## The NASA STI Program Office . . . in Profile

Since its founding, NASA has been dedicated to the advancement of aeronautics and space science. The NASA Scientific and Technical Information (STI) Program Office plays a key part in helping NASA maintain this important role.

The NASA STI Program Office is operated by Langley Research Center, the Lead Center for NASA's scientific and technical information. The NASA STI Program Office provides access to the NASA STI Database, the largest collection of aeronautical and space science STI in the world. The Program Office is also NASA's institutional mechanism for disseminating the results of its research and development activities. These results are published by NASA in the NASA STI Report Series, which includes the following report types:

- **TECHNICAL PUBLICATION.** Reports of completed research or a major significant phase of research that present the results of NASA programs and include extensive data or theoretical analysis. Includes compilations of significant scientific and technical data and information deemed to be of continuing reference value. NASA's counterpart of peer-reviewed formal professional papers but has less stringent limitations on manuscript length and extent of graphic presentations.
- **TECHNICAL MEMORANDUM.** Scientific and technical findings that are preliminary or of specialized interest, e.g., quick release reports, working papers, and bibliographies that contain minimal annotation. Does not contain extensive analysis.
- **CONTRACTOR REPORT.** Scientific and technical findings by NASA-sponsored contractors and grantees.

- **CONFERENCE PUBLICATION.** Collected papers from scientific and technical conferences, symposia, seminars, or other meetings sponsored or cosponsored by NASA.
- **SPECIAL PUBLICATION.** Scientific, technical, or historical information from NASA programs, projects, and missions, often concerned with subjects having substantial public interest.
- **TECHNICAL TRANSLATION.** English-language translations of foreign scientific and technical material pertinent to NASA's mission.

Specialized services that complement the STI Program Office's diverse offerings include creating custom thesauri, building customized databases, organizing and publishing research results . . . even providing videos.

For more information about the NASA STI Program Office, see the following:

- Access the NASA STI Program Home Page at <http://www.sti.nasa.gov>
- E-mail your question via the Internet to [help@sti.nasa.gov](mailto:help@sti.nasa.gov)
- Fax your question to the NASA Access Help Desk at 301-621-0134
- Telephone the NASA Access Help Desk at 301-621-0390
- Write to:  
NASA Access Help Desk  
NASA Center for Aerospace Information  
7121 Standard Drive  
Hanover, MD 21076



# Oxidation-Reduction Resistance of Advanced Copper Alloys

L. Thomas-Ogbuji and D.L. Humphrey  
QSS Group, Inc., Cleveland, Ohio

J.A. Setlock  
Case Western Reserve University, Cleveland, Ohio

Prepared for the  
International Symposium on Corrosion Science in the 21st Century  
cosponsored by the CAPCIS, Ltd. and the Office of Naval Research International Field Office  
Manchester, United Kingdom, July 6–11, 2003

Prepared under Contract NAS3–98008

National Aeronautics and  
Space Administration

Glenn Research Center

This report is a formal draft or working paper, intended to solicit comments and ideas from a technical peer group.

Trade names or manufacturers' names are used in this report for identification only. This usage does not constitute an official endorsement, either expressed or implied, by the National Aeronautics and Space Administration.

Available from

NASA Center for Aerospace Information  
7121 Standard Drive  
Hanover, MD 21076

National Technical Information Service  
5285 Port Royal Road  
Springfield, VA 22100

Available electronically at <http://gltrs.grc.nasa.gov>

# **Oxidation-Reduction Resistance of Advanced Copper Alloys**

L. Thomas-Ogbuji\* and D.L. Humphrey  
QSS Group, Inc.  
Cleveland, Ohio 44135

J.A. Setlock  
Case Western Reserve University  
Cleveland, Ohio 44106

## **Abstract**

Resistance to oxidation and blanching is a key issue for advanced copper alloys under development for NASA's next-generation of reusable launch vehicles. Candidate alloys, including dispersion-strengthened Cu-Cr-Nb, solution-strengthened Cu-Ag-Zr, and ODS Cu-Al<sub>2</sub>O<sub>3</sub>, are being evaluated for oxidation resistance by static TGA exposures in low-p(O<sub>2</sub>) and cyclic oxidation in air, and by cyclic oxidation-reduction exposures (using air for oxidation and CO/CO<sub>2</sub> or H<sub>2</sub>/Ar for reduction) to simulate expected service environments. The test protocol and results are presented.

## **Introduction**

Due to their high thermal conductivity, copper alloys make excellent liners for the hot sections of high-heat-flux engines, such as combustion chambers of rocket engines for launching space payloads. However, in that aggressive service environment Cu alloys are prone to degradation by oxidation-related phenomena. In a combustor there are always issues of static and cyclic oxidation; in a hydrogen-fueled ("LH<sub>2</sub>-LOX") rocket engine there is the additional issue of blanching, which causes the most serious oxidation-related damage to the liners [1–4]. Blanching is caused by spatial and temporal variations in oxidant-to-fuel (O/F) ratio, which change the local ambient from oxidizing to reducing and back [3]. Oxide film formed in the fuel-lean cycle is reduced and removed in the fuel-rich cycle, thus exposing the metal to further attack. Therefore, blanching is somewhat analogous to cyclic oxidation, except that the duration of an oxidation-reduction cycle may be in microseconds, rather than the minutes or hours that characterize cyclic oxidation. The "blanched" (i.e., bleached) spots indicate accelerated degradation, which has serious consequences for the impairment of cooling systems beneath the liner. Thus, evaluation of copper alloys for oxidative degradation involves tests for static oxidation, cyclic oxidation, and oxidation-reduction resistance.

Advanced copper alloys of interest to aerospace engine makers (as liners for thrust cell combustion chambers and nozzle ramps) are under study at NASA and in industry. They include: Cu-8Cr-4Nb, developed by the NASA Glenn Research Center in conjunction with Case Western Reserve University (designated "GRCop-84"); Cu-3Ag-0.1Zr ("NARloy-Z", which is the current Space Shuttle Main Engine liner material); and Cu-0.1Zr ("Amzirc"). Cu-8Cr-4Nb is a dispersion-strengthened alloy, comprised of a Cu matrix with a 14 vol% dispersion of insoluble Cr<sub>2</sub>Nb precipitates [5]; the other two are solution-strengthened alloys. All are of interest to thrust-cell designers because of their very good thermal and mechanical properties, especially at

---

\*Phone: 216-433-6463; E-mail: [thomas-ogbuji@grc.nasa.gov](mailto:thomas-ogbuji@grc.nasa.gov)

elevated temperatures. These alloys, along with Cu-Al<sub>2</sub>O<sub>3</sub> (“Glidcop”, an ODS alloy) have been evaluated for resistance to oxidative degradation, as part of NASA’s program for next-generation launch technology (NGLT). The ODS alloy has a nano-scale dispersion of Al<sub>2</sub>O<sub>3</sub> in Cu; there are three versions, with 15, 25, and 60 wt% Al (0.3, 0.5, and 1.1 wt% Al<sub>2</sub>O<sub>3</sub>, respectively), designated Glidcop “AL-15,” “AL-25,” and “AL-60,” respectively. The evaluation performed in this study included static oxidation by TGA in various oxygen partial pressures dictated by the thermodynamics of a LOX/LH2 engine, cyclic oxidation in air, and oxidation-reduction experiments conducted by in-situ switching between oxidant and reductant gases for various programmed durations.

## Experimental Details

The materials were powder metallurgy (PM) alloys, extruded and rolled to develop optimum mechanical properties. Samples for oxidation testing were cut into rectangular or circular coupons 1 mm thick, with 19 mm as their largest dimensions, and polished to 1000-grit finish; those for oxidation-reduction were cut into mini-disks 5 to 7 mm in diameter and polished wafer-thin to a mirror finish.

Static TGA oxidation was conducted in oxygen diluted with argon to desired O<sub>2</sub> concentrations ranging from 0.033 vol% to 100% O<sub>2</sub>, at temperatures of 550 to 850 °C; oxidation durations were 10 to 50 hr. Cyclic oxidation was done in air at 500 to 700 °C, each run consisting of twenty half-hour cycles (for total exposure times of 10 hr) with the samples weighed on every cycle. For blanching simulation the mini-disks were cycled at 800 °C between air and reducing gas. This reductant was initially 90% CO/10% CO<sub>2</sub>, later 5% H<sub>2</sub> in Ar (5% being the maximum hydrogen concentration permitted by safety considerations). All gases were of ultra-high-purity grade. The oxidation-reduction schedule was: 0.5 hr to heat to 800 °C in H<sub>2</sub>/Ar, ~3 hr of oxidation-reduction cycling, and 1 hr of cooling to room temperature in H<sub>2</sub>/Ar.

One oxidation-reduction cycle consisted of exposure for  $t_O$  minutes in air followed by  $t_R$  minutes in H<sub>2</sub>/Ar. Switching between the two environments was done in-situ. The values of  $t_O$  and  $t_R$  were optimized to satisfy two criteria: (1) that a detectable quantity of oxide be observed to grow in the oxidation half-cycle and then to be fully consumed in the reduction half-cycle thereby exposing the substrate for further reaction; and (2) that a large number of cycles be accommodated in a 5 hr experiment, for maximum cumulative effect. In practice this amounted to fixing  $t_O$  at a low value and increasing  $t_R$  until both criteria were satisfied. The values of  $t_O$  and  $t_R$ , respectively, that gave satisfactory results are 0.5 and 5 minutes for reduction in CO/CO<sub>2</sub>; for reduction in 5%H<sub>2</sub>/Ar they were 0.1 and 5 minutes. This need to amplify the oxidation and reduction effects also necessitated doing the test at the rather high temperature of ~800 °C, rather than the wall temperature of ~600 to 700 °C expected in service.

## Results and Discussion

### Static Oxidation

TGA results for the Cu alloys are compared in Fig. 1 for a representative set of conditions. Note that: (1) 700 °C is in the upper reaches of expected service temperatures, and oxidation rates and mechanisms were found to be independent of  $p(O_2)$  in the range of 0.25 to 100% O<sub>2</sub> [6]. (2) Cu and the two solution-strengthened alloys are in one class, with very similar oxidation rates;




Fig. 1. Oxidation kinetics in 2.2% O<sub>2</sub> at 700 °C, illustrating parabolic behavior for Cu and the alloys at all temperatures investigated and in 0.25 vol% to 100% O<sub>2</sub>

and the dispersion-strengthened alloys (Cu-8Cr-4Nb and Cu-Al<sub>2</sub>O<sub>3</sub>) in another class with much lower oxidation rates. (3) The kinetics are parabolic for all the alloys (and stayed so for temperatures and in all ambients with 0.25% and higher O<sub>2</sub> concentrations).

The uniformly parabolic kinetics are consistent with the fact that the major event occurring in each case is oxidation of Cu to its usual duplex oxide (Cu<sub>2</sub>O/CuO), which is controlled by diffusion of Cu through the oxide. In Cu and the solution-strengthened alloys, this conversion of Cu to Cu<sub>2</sub>O/CuO remains the sole oxidation process involved. In the dispersion-strengthened alloys, on the other hand, the overall rate is controlled by processes no doubt involving the dispersoids. For Cu-8Cr-4Nb that process is a modified reservoir effect resulting from oxidation of Cr<sub>2</sub>Nb [6]; the sub-layer of Cr-Nb oxides is indicated in Fig. 2, and beneath it is a characteristic precipitate-free zone in the substrate. For Cu-Al<sub>2</sub>O<sub>3</sub> it appears that the slow oxidation kinetics must relate to the presence of nano-dispersed Al<sub>2</sub>O<sub>3</sub>, but the exact details remain as yet unidentified. Fuller accounts of these observations appear elsewhere [6].

### Temperature Cycling

Figure 3(a) shows cyclic-oxidation weight changes for several Cu alloys. The disparity among the three Cu-Al<sub>2</sub>O<sub>3</sub> compositions (ODS-15, 25, and 60), which differ in only their Al<sub>2</sub>O<sub>3</sub> contents, is unexplained. Apart from that disparity, and the insignificant weight change of pure




Fig. 2. SEM cross-section of Cu-8Cr-4Nb oxidized in air at 700 °C, showing oxide/substrate boundary: FOL (friable oxide layer) is inner layer of  $\text{Cu}_2\text{O}$ ; DOL (dense oxide layer) is a layer of Cr-Nb oxides; PFZ is a precipitate-free zone induced in the matrix by oxidation.




Fig. 3a. Cyclic-oxidation weight changes in air at 600 °C.






Fig. 3(b).Cu alloys after 10 hr of cyclic oxidation in air at 600 °C. Cu-8Cr-4Nb, which had the lowest weight change in Fig. 3(a), also shows the fullest oxide cover in Fig. 3(b).

These 600 °C cyclic-oxidation results are representative of the results obtained at the other temperatures: the dispersion-strengthened alloys resisted cyclic oxidation (i.e., exhibited the least weight changes) better than the solution-strengthened alloys, and good performance in this regard correlated with retention of oxide scale through the cycles.

#### **Oxidation-Reduction Cycling**

Figure 4 shows the weight-change responses of Cu-8Cr-4Nb and Cu-3Ag-0.5Zr (which is known to undergo blanching) during oxidation-reduction. The oxidation was performed in air and the reduction in CO/CO<sub>2</sub> or H<sub>2</sub>/Ar as indicated in the figure. The responses are qualitatively the same for the two different reductants. Cu-3Ag-0.5Zr, which is prone to blanching, is characterized by a flat weight-gain response (after the ~20 minutes it took to attain exposure




Fig. 4. Weight-change profiles for Cu-3Ag-0.5Zr and Cu-8Cr-4Nb during oxidation-reduction exposures at 800 °C. In each case air was the oxidant and CO or H2 the active reductant, as indicated.

temperature). Thus, for this material, weight gained during the oxidation stage of a cycle was completely lost during the reducing stage. In contrast, Cu-8Cr-4Nb is characterized by continuous weight gain, reaching saturation after ~2 hr.

The appearance of the samples after oxidation-reduction also correlated with the above weight-gain profiles: Cu-3Ag-0.5Zr coupons emerged with a clean, metallic luster while Cu-8Cr-4Nb coupons came out dark.

Shown in Fig. 5 are SEM images of the sample surfaces: Cu-3Ag-0.5Zr was deeply pitted and scarred, while Cu-8Cr-4Nb was fully covered in a mat identified by EDS as oxides of Cr and Nb, as detailed elsewhere [7]. It seems these Cr-Nb-O phases resist reduction and hence protect the substrate from further degradation. In other words, to the extent that oxidation-reduction is a key factor in blanching attack, this alloy should resist blanching at the temperatures where Cr-Nb oxides grow [7].

## Summary and Conclusion

In an effort to assess, by laboratory means, the blanching resistance of an advanced Cu alloy, Cu-8Cr-4Nb, this material was subjected to 40 to 50 in-situ cycles of oxidation-reduction. The same treatment was given to Cu-3Ag-0.5Zr, an alloy that is known to undergo blanching degradation in service as a rocket engine liner. Cu-3Ag-0.5Zr, which usually forms a  $\text{Cu}_2\text{O}/\text{CuO}$  scale, registered zero net weight gain during the exposure; the sample emerged without oxide cover, its surface deeply sculpted in a manner consistent with blanching features usually observed




Fig. 5. SEM images of (a) Cu-3Ag-0.5Zr and (b) Cu-8Cr-4Nb surfaces after oxidation-reduction cycling: The former is bare, with deep fissures (shown at higher magnification) indicative of extensive attack, while the later is covered by protective oxide.

in service. In contrast, Cu-8Cr-4Nb (which usually forms an additional subscale of Cr-Nb oxides) registered continuous weight gain, and the sample emerged with a protective cover of Cr-Nb oxides which are resistant to reduction.

Cu-8Cr-4Nb is very likely to resist blanching degradation in service since it has been shown in this study to resist oxidation-reduction, and also shown (elsewhere) to resist static and cyclic oxidation much better than Cu-3Ag-0.5Cr).

## References

1. D.B. Morgan and J.E. Franklin, "Hot-Fire Test Investigation of Copper Combustion Chamber Blanching," NASA Contract Report NAS 8-36167 of August 1989.
2. D.B. Morgan, T. Nguyentat, J.E. Franklin, and A.C. Kobayashi, "Investigation of Copper Alloy Combustion Chamber Degradation by Blanching," Advanced Earth-to-Orbit Propulsion Tech., (1988) vol. II, R. Richmond & S.T. Wu. eds. Marshall Space Flight Center, Huntsville, Alabama (1988).
3. M. Murphy, R.E. Anderson, D.C. Rousar, and J.A. VanKleeck, "Effects of Oxygen/Hydrogen Combustion Chamber Environment on Copper Alloys," Advanced Earth-to-Orbit Propulsion Technology, (1986) vol. II, R. Richmond & S.T. Wu. eds. Marshall Space Flight Center, Huntsville, Alabama (1988).
4. R.J. Quentmeyer, "Thrust Chamber Thermal Barrier Coating Techniques," NASA Tech. Memo. 100933 (Presented at 72nd Specialists' Meeting of the Propulsion and Energetics Panel at Bath, U.K., Oct 1988).
5. Dave Ellis etc. (on GRCop-84).
6. L.U. Ogbuji, D.L. Humphrey, and J.A. Setlock, "Comparison of the Oxidation Rates of Some New Copper Alloys" (to appear in Oxidation of Metals).
7. L.U. Ogbuji, "The General Isothermal Oxidation behavior of Cu-8Cr-4Nb" (to appear in Materials at High Temperatures).

REPORT DOCUMENTATION PAGE			Form Approved OMB No. 0704-0188	
Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503.				
1. AGENCY USE ONLY (Leave blank)		2. REPORT DATE August 2003		3. REPORT TYPE AND DATES COVERED Final Contractor Report
4. TITLE AND SUBTITLE  Oxidation-Reduction Resistance of Advanced Copper Alloys			5. FUNDING NUMBERS  WBS-22-721-26-06 NAS3-98008	
6. AUTHOR(S)  L. Thomas-Ogbuji, D.L. Humphrey, and J.A. Setlock				
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES)  QSS Group, Inc. 21000 Brookpark Road Cleveland, Ohio 44135			8. PERFORMING ORGANIZATION REPORT NUMBER  E-14115	
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES)  National Aeronautics and Space Administration Washington, DC 20546-0001			10. SPONSORING/MONITORING AGENCY REPORT NUMBER  NASA CR-2003-212549	
11. SUPPLEMENTARY NOTES Prepared for the International Symposium on Corrosion Science in the 21st Century cosponsored by the CAPCIS, Ltd. and the Office of Naval Research International Field Office, Manchester, United Kingdom, July 6-11, 2003. L. Thomas-Ogbuji and D.L. Humphrey, QSS Group, Inc., Cleveland, Ohio 44135; and J.A. Setlock, Case Western Reserve University, Cleveland, Ohio 44106. Project Manager, L. Greenbauer-Seng, Materials Division, NASA Glenn Research Center, organization code 5160, 216-433-6781.				
12a. DISTRIBUTION/AVAILABILITY STATEMENT  Unclassified - Unlimited Subject Category: 10  Available electronically at <a href="http://gltrs.grc.nasa.gov">http://gltrs.grc.nasa.gov</a> This publication is available from the NASA Center for AeroSpace Information, 301-621-0390.			12b. DISTRIBUTION CODE	
13. ABSTRACT (Maximum 200 words)  Resistance to oxidation and blanching is a key issue for advanced copper alloys under development for NASA's next-generation of reusable launch vehicles. Candidate alloys, including dispersion-strengthened Cu-Cr-Nb, solution-strengthened Cu-Ag-Zr, and ODS Cu-Al <sub>2</sub> O <sub>3</sub> , are being evaluated for oxidation resistance by static TGA exposures in low-p(O <sub>2</sub> ) and cyclic oxidation in air, and by cyclic oxidation-reduction exposures (using air for oxidation and CO/CO <sub>2</sub> or H <sub>2</sub> /Ar for reduction) to simulate expected service environments. The test protocol and results are presented.				
14. SUBJECT TERMS  Copper alloys; Blanching oxidation; Oxidation-reduction; Cu alloys; Blanching degradation			15. NUMBER OF PAGES 14	
			16. PRICE CODE	
17. SECURITY CLASSIFICATION OF REPORT  Unclassified	18. SECURITY CLASSIFICATION OF THIS PAGE  Unclassified	19. SECURITY CLASSIFICATION OF ABSTRACT  Unclassified	20. LIMITATION OF ABSTRACT	